

MANUFACTURER

STONEPRO TRADING CORPORATION
 Address : 176 H Tandang Sora Ave. Quezon City, Philippines 1116
 Contact no.: (02) 929 3116 / 927 3086 / 621 9075
 Mobile no.: 0922 868 0806 / 0917 893 4908 Fax : 930 4142 / 621 9075
 Website : www.gtstoneworks.com.ph

PRODUCT NAME

FORTRESS SKIM COAT SUPERFINE WHITE

PRODUCT DESCRIPTION

FORTRESS SKIM COAT is a specially formulated skimcoat mixture designed for thin plastering applications. It offers excellent non-sag properties that provide easy applications for overhead and wall areas.

SURFACE PREPARATION

The concrete surface must be structurally sound, clean and free from loose concrete, dirt, form oils and other chemical contaminants, Wet surfaces well with clean water prior to application of FORTRESS SKIM COAT especially on exposed areas.

COVERAGE

Approximately 1 kilo of FORTRESS SKIM COAT from one (1)mm to four (4)mm thick per sqm, depending on surface condition, profile and type of skim coat.

SHELF LIFE

Store in a cool dry place. FORTRESS SKIM COAT will remain usable for a period of 6 to 12 months from date of manufacture.

ADVANTAGES

- ✓ Corrects Uneven Surfaces
- ✓ Professional Finish
- ✓ Crack Resistant
- ✓ Budget Friendly
- ✓ Moisture Barrier Protection
- ✓ Paintable
- ✓ For Indoor & Outdoor use



FAST AND EASY JUST ADD WATER

COLOR

White & Gray

TECHNICAL DATA

Solubility in water	slight 3% maximum
Specific gravity	0.99
Odor	no odor
Water retentivity	99.9%
Average Compressive Strength	25.0 N/mm
Average shrinkage	0.10%
Tensile adhesion strength	2.2 N/mm (14 days)
	2.1 N/mm (QUV)
Loss of tensile adhesion strength after QUV	4.5%

CAUTION

Use gloves and eye protection. Avoid contact with eyes and prolonged skin contact. If eye contact occurs, wash with clean water and consult a doctor immediately.

WARRANTY

FORTRESS SKIM COAT is covered from the date of purchase when used on substrate which conforms to local building codes and when installed, in accordance with the manufacturer's instruction. FORTRESS SKIM COAT will replace those which are determined to be defective. This warranty is limited to the original purchaser and may not be transferred to any subsequent owner. This warranty does not cover damage resulting from: settlement of the building or other wall movement, mixing with other chemicals or additives and prolonged exposure to heat and other irregular temperature. This warranty covers only manufacturing defects in FORTRESS SKIM COAT. It will not cover labor costs or damages obtained from removal and replacement of defective products.

MIXING AND APPLICATION



1. Mix the required quantity of FORTRESS SKIM COAT with clean water in a plastic container. A ratio of 1.00 part FORTRESS SKIM COAT and 0.30 part water is recommended.

MIXING RATIO

7-8 LITERS + 20 KGS SKIM COAT

POT LIFE

3-4 HOURS



2. Mix thoroughly until paste becomes free from any lumps. For best results, allow mixtures to stand for 5 minutes before application. Do not add any more water after final mixing.

FOR BEST RESULT

USE MIXING TORQUE



3. Prepare the surface by removing all dirt, oil, dust and other contaminants. Damp the surface using clean water until absorption stops. apply FORTRESS SKIM COAT using hand trowel.

OPEN TIME

15 MINUTES



4. To increase thickness of FORTRESS SKIM COAT, apply the second coat when first coat has set. After curing time of 24 hours, surfaces can be sanded for a flatter, even surface.

RECOMMENDED INSTALLATIONS INSTRUCTION FOR A PERFECT WALL FINISH

STEP 1



Apply scratch coat plaster on CHB wall with a thickness of 12mm.

STEP 2



Use FORTRESS SKIM COAT to finish the masonry

STEP 3



Apply final paint finish

PACKAGING

